

Guaranteed Specifications (wt% by XRF)

Grade	ZCO-1	ZCO-2	ZCO-3H	ZCO-3L	ZCO-4
ZrO ₂ +HfO ₂ (%) ¹	≥95.0	>96.6	>98.0	>98.5	>98.5
SiO ₂ (%)	<4.0	<2.5	<1.0	<0.6	<0.35
Al ₂ O ₃ (%)	≤0.6	≤0.6	≤0.5	≤0.5	≤0.50
Fe ₂ O ₃ (%)	≤0.10	≤0.10	≤0.10	≤0.10	≤0.10
TiO ₂ (%)	≤0.25	≤0.25	≤0.25	≤0.25	≤0.25

Typical Chemical Analysis (wt% by XRF)

Grade	ZCO-1	ZCO-2	ZCO-3H	ZCO-3L	ZCO-4
ZrO ₂ +HfO ₂ (%) ¹	95.6	97.3	98.5	98.6	99.0
SiO ₂ (%)	3.5	2.0	0.8	0.5	0.24
Al ₂ O ₃ (%)	0.5	0.5	0.4	0.4	0.37
Fe ₂ O ₃ (%)	0.05	0.05	0.03	0.03	0.02
TiO ₂ (%)	0.15	0.15	0.15	0.15	0.15
BaO (%)	0.01	0.01	0.01	0.01	0.01
CaO (%)	0.02	0.02	0.02	0.02	0.02
U+Th (ppm)	≤550	≤550	≤550	≤550	≤550
Specific Activity (Bq/g) ²	3.4 – 4.3	3.4 – 4.3	3.4 – 4.3	3.4 – 4.3	3.4 – 4.3

¹ Calculated by difference

² Specific Activity is calculated from the U & Th assay

Typical Physical Properties

Specific Surface Area	1 m ² /g
Tapped Bulk Density	2.0 g/cm ⁻³
Loose Bulk Density	1.8 g/cm ⁻³
Specific Gravity	5.75 g/cm ⁻³
Crystal Structure	monoclinic
Moisture	0.1%
LOI	0.1%

Radioactivity

ZCO contains low levels of U and Th (U + Th ~ 550ppm, ~4.5 Bq/g). When following recommended safe handling practices, radiation exposure is unlikely to exceed 0.3mSv/year. ZCO containing lower levels of U and Th are also available.

Other Information

See www.doral.com.au for Material safety data sheet

EINECS NO. 215-227-2

CAS NO. 1314-23-4

Packing

Standard packing is in 1 tonne bulk bags or 25kg multi-wall paper bags.

Milled product batches can be blended in 5 tonne lots for consistency of chemistry.

Contact Details

To obtain further information about our products, please send an email to doral@doral.com.au

Contact: **Graeme O'Grady**
Group Marketing Manager
 Phone: +61 8 9439 8835 Fax: +61 8 9439 2892
 Email: graeme.ogrady@doral.com.au

Contact: **Lloyd Kaiser**
Marketing Manager – Global Development
 Phone: +61 8 9439 8838 Fax: +61 8 9439 2892
 Email: lloyd.kaiser@doral.com.au

Document: PDS-011d – DFM – ZCO General
 Last reviewed on 16/06/2010

Information herein is given in good faith as authoritative and valid,
 However no warranty, expressed or implied can be made.